

Hydrolack DM 100

Matt Overprint Varnish - Water based

Description:

Matt Overprint Varnish for paper and carton with a good drying speed. With the appropriate selection of the substrate a smooth matt finish with a good scuff and block resistance can be achieved. Dries without streaking, does not effect colour performance of the ink.

Application:

With varnishing units on sheet fed presses a wet film of 3-6 g/m² is recommended for most cartons. Higher film weights are achievable with the appropriate drying equipment. Mix well before use! Storage not above 34°C. Protect from freezing! Check viscosity before use.

Technical Datas:

Viscosity:	35-40 seconds DIN cup No. 4 at 24°C
Gloss:	Matt, below 20% (Gloss meter 60°)
Drying Speed:	High
Rub resistance:	Good
Slip:	Good
pH-value:	7,7 - 8,4
Work and Turn:	Yes
Gluable:	Yes

Packaging:

10/20 kg Can, 120/220 kg Drum, 1.000 kg IBC

