

# Hydrolack DH 211

Highgloss Overprint Varnish - Water based

## Description:

High Gloss Overprint Varnish for paper and carton with a good drying speed. With the appropriate selection of the substrate a gloss level comparable to UV varnish can be achieved.

## Application:

With varnishing units on sheet fed presses a wet film of 3-6 g/m<sup>2</sup> is recommended for most cartons. Higher film weights are achievable with the appropriate drying equipment. Mix well before use! Storage not above 34°C. Protect from freezing! Check viscosity before use.

## Technical Datas:

Viscosity:	35-40 seconds DIN cup No. 4 at 24°C
Gloss:	Above 60%
Drying Speed:	Medium
Rub resistance:	Good
Slip:	Good
pH-value:	7,7 - 8,4
Work and Turn:	No
Gluable:	Yes

## Packaging:

10/20 kg Can, 120/220 kg Drum, 1.000 kg IBC

